## L.V.T. Moduleo Transform Square Tile

## **Specifications:**

Level of use ISO 10874 -23 - 33Total thickness -2.50 mmWear layer PUR treatment -Protectonite®Total weight -4059 g/m²Tiles (Square) -49.30 x 49.30 cmBox tiles (Square) -14 pc/box, 3.40m²/boxInflammability EN 13501-1 -Bfl-S1Critical Radiant Flux EN ISO 9239-1 -8.1 kW/m2Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35$ mmSlip resistance -D5Slip resistance -D5Slip resistance -Norm: $\leq 0.10$ mm, Average result measured $\leq 0.03$ mmFurniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25$ %, Average result measured $\leq 0.05$ %Heat insulation - $0.27$ w/(m.K)Thermal resistance R - $0.0100$ m² K/WElectrostatic performance - $< 2$ kVAcoustic insulation - $3$ dBCattor chair resistance -No damage to wearlayer, no delamination	Dimensional stability		$\begin{array}{c c} \hline \\ \hline $
Wear layer - $0.55 \text{ mm}$ Wear layer PUR treatment -Protectonite®Total weight - $4059 \text{ g/m}^2$ Tiles (Square) - $49.30 \times 49.30 \text{ cm}$ Box tiles (Square) - $14 \text{ pc/box}, 3.40\text{m}^2/\text{box}$ Inflammability EN 13501-1 -Bfl-S1Critical Radiant Flux EN ISO 9239-1 - $8.1 \text{ kW/m2}$ Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -No cracks, no damageDimensional stability - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $< 2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$	Level of use ISO 10874 -		23 - 33
Wear layer PUR treatment -Protectonite®Total weight - $4059 \text{ g/m}^2$ Tiles (Square) - $49.30 \times 49.30 \text{ cm}$ Box tiles (Square) - $14 \text{ pc/box}, 3.40\text{m}^2/\text{box}$ Inflammability EN 13501-1 -Bfl-S1Critical Radiant Flux EN ISO 9239-1 - $8.1 \text{ kW/m2}$ Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25 \%$ , Average result measured $\leq 0.05 \%$ Heat insulation - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $< 2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$	Total thickness -		2.50 mm
Total weight - $4059 \text{ g/m}^2$ Tiles (Square) - $49.30 \times 49.30 \text{ cm}$ Box tiles (Square) - $14 \text{ pc/box}, 3.40\text{m}^2/\text{box}$ Inflammability EN 13501-1 -Bfl-S1Critical Radiant Flux EN ISO 9239-1 - $8.1 \text{ kW/m2}$ Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -No cracks, no damageDimensional stability - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$	Wear layer -		0.55 mm
Tiles (Square) -49.30 x 49.30 cmBox tiles (Square) -14 pc/box, $3.40m^2/box$ Inflammability EN 13501-1 -Bfl-S1Critical Radiant Flux EN ISO 9239-1 - $8.1 kW/m2$ Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 mm$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 mm$ , Average result measured $\leq 0.03 mm$ Furniture leg resistance -No cracks, no damageDimensional stability - $0.27 w/(m.K)$ Thermal resistance R - $0.0100 m^2 K/W$ Electrostatic performance - $2 kV$ Acoustic insulation - $3 dB$	Wear layer PUR treatmen	ıt -	
Box tiles (Square) -14 pc/box, $3.40m^2/box$ Inflammability EN 13501-1 -Bfl-S1Critical Radiant Flux EN ISO 9239-1 - $8.1 \text{ kW/m2}$ Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -Do cracks, no damageDimensional stability -Norm: $\leq 0.25 \%$ , Average result measured $\leq 0.05 \%$ Heat insulation - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $< 2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$	Total weight -		4059 g/m <sup>2</sup>
Inflammability EN 13501-1 -Bfl-S1Critical Radiant Flux EN ISO 9239-1 - $8.1 \text{ kW/m2}$ Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25 \%$ , Average result measured $\leq 0.05 \%$ Heat insulation - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$	Tiles (Square) -		
Critical Radiant Flux EN ISO 9239-1 - $8.1 \text{ kW/m2}$ Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25 \%$ , Average result measured $\leq 0.05 \%$ Heat insulation - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $< 2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$	Box tiles (Square) -		
Scratch resistance EN 16094-MSR-A2, MSR- B1Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25$ %, Average result measured $\leq 0.05$ %Heat insulation - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $< 2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$			
Squareness & straightness - $\leq 0.35 \text{ mm}$ Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10 \text{ mm}$ , Average result measured $\leq 0.03 \text{ mm}$ Furniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25 \%$ , Average result measured $\leq 0.05 \%$ Heat insulation - $0.27 \text{ w/(m.K)}$ Thermal resistance R - $0.0100 \text{ m}^2 \text{ K/W}$ Electrostatic performance - $< 2 \text{ kV}$ Acoustic insulation - $3 \text{ dB}$			
Slip resistance -DSSlip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10$ mm, Average result measured $\leq 0.03$ mmFurniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25$ %, Average result measured $\leq 0.05$ %Heat insulation - $0.27$ w/(m.K)Thermal resistance R - $0.0100$ m² K/WElectrostatic performance - $< 2$ kVAcoustic insulation - $3$ dB			· · · · · · · · · · · · · · · · · · ·
Slip restraint EN 16165 annex B -R10Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10$ mm, Average result measured $\leq 0.03$ mmFurniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25$ %, Average result measured $\leq 0.05$ %Heat insulation - $0.27$ w/(m.K)Thermal resistance R - $0.0100$ m² K/WElectrostatic performance - $< 2$ kVAcoustic insulation - $3$ dB			
Residual indentation EN ISO 24343-1 -Norm: $\leq 0.10$ mm, Average result measured $\leq 0.03$ mmFurniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25$ %, Average result measured $\leq 0.05$ %Heat insulation - $0.27$ w/(m.K)Thermal resistance R - $0.0100$ m² K/WElectrostatic performance - $< 2$ kVAcoustic insulation - $3$ dB			
Furniture leg resistance -No cracks, no damageDimensional stability -Norm: $\leq 0.25$ %, Average result measured $\leq 0.05$ %Heat insulation - $0.27$ w/(m.K)Thermal resistance R - $0.0100$ m² K/WElectrostatic performance - $< 2$ kVAcoustic insulation - $3$ dB			
Dimensional stability -Norm: $\leq 0.25$ %, Average result measured $\leq 0.05$ %Heat insulation - $0.27$ w/(m.K)Thermal resistance R - $0.0100$ m² K/WElectrostatic performance - $< 2$ kVAcoustic insulation - $3$ dB			
Heat insulation -0.27 w/(m.K)Thermal resistance R -0.0100 m² K/WElectrostatic performance -< 2 kV			
Thermal resistance R -0.0100 m² K/WElectrostatic performance -< 2 kV			
Electrostatic performance - < 2 kV			
Acoustic insulation - 3 dB			
	•		
	Castor chair resistance -		
	Formaldehyde Group EN 717-1		
	Stain resistance -		
Light fastness - ≥6			
Underfloor heating - Suitable, max 27°C			
Wear Warranty (year) - 25 Residential / 10 Commercial			

• RUBBER MIGRATION: This is a condition that can cause vinyl to discolour. Migration occurs when latex or rubber products such as shoes, rubber backed mats or rubber soled slippers come into contact with vinyl over a period of time. This is not a manufacturing fault and therefore is not covered under our warranties.

• Warranties are extended to the original purchaser of the product only and are not transferable.

Please contact us on 03 366 9839 to request any samples or other product details.

international flooring solutions

**p** 03 366 9839 **e** office@robertmalcolm.co.nz 10 Establishment Drive, PO Box 914, Christchurch 8140, New Zealand **robertmalcolm.co.nz** 

## robert malcolm