

# Residential Vinyl Status

## Specifications:




Domestic  
medium




Commercial  
general



Slip  
resistant



Reduces  
noise



Light  
fastness



Thermal  
resistance



Chemical  
resistant



	240 Quality	260 Quality
European classification EN ISO 10874 -	23 / 41	22 / 22+
Total thickness -	2.40 mm	2.60 mm
Wear layer -	0.35 mm	0.22 mm
Total weight -	1580 g/m <sup>2</sup>	1475 g/m <sup>2</sup>
Width -	2 m & 3 m	2 m & 3 m
Slip resistance DIN 51130 -	R10	R 9 & R 10 depending on structure
Inflammability -	Cfl-S1	Cfl-S1
Critical radiant flux ISO 9239.1:2010 -	6.40 KW/m <sup>2</sup>	6.90 KW/m <sup>2</sup>
Acoustical insulation EN ISI 717-2 -	16 dB	20 dB
Light fastness ISO 105-B02 -	≥ 6	≥ 6
Underfloor heating -	Suitable	
Thermal resistance ISO 10456 -	0.03 m <sup>2</sup> /kW	0.04 m <sup>2</sup> /kW
Resistance to household chemicals -	OK	
Residual indentation EN ISO 24343-1	≤ 0.20 mm	≤ 0.25 mm
Dimensional stability EN ISO 23999 -	≤ 0.15	≤ 0.15
Formaldehyde group EN 717-1 -	E1	E1
Total VOC emissions EN 16516 -	Gold	Gold
Warranty (year) -	15 years (Residential use)	10 years (Residential use)

- RUBBER MIGRATION: This is a condition that can cause vinyl to discolour. Migration occurs when latex or rubber products such as shoes, rubber backed mats or rubber soled slippers come into contact with vinyl over a period of time. This is not a manufacturing fault and therefore is not covered under our warranties.
- Warranties are extended to the original purchaser of the product only and are not transferable.

Please contact us on 03 366 9839 to request any samples or other product details.

international  
flooring solutions

p 03 366 9839 e office@robertmalcolm.co.nz  
10 Establishment Drive, PO Box 914, Christchurch 8140, New Zealand  
robertmalcolm.co.nz



robert malcolm